

REBAflow 201 (FM)

Superplasticizer according to EN 934-2:T3.1/3.2

Industrial use

Product No.: 250009010

Product Information:

Properties:

- high-performance superplasticizer with longer workability time
- high final strength of concrete with low water/cement ratio

Application:

admixture for the consistency classes F3 to F6
precast concrete elements
ready-mix concrete

Efficiently lowering the clinker factor makes it possible to reduce CO₂ emissions.

A reduction in the clinker factor in cement from 0.73 to 0.5 means a reduction of > 200 kg/CO₂ per tonne of cement (calculation basis = approx. 750 kg to 800 kg CO₂ per tonne of clinker).

The life cycle assessment data and the other contents of the sample EPD can be used to assess the sustainability of buildings in which the product has been installed.

Sustainability Assessment:

Reduction of the clinker factor in the cement
Reducing the water-cement ratio and increasing the durability of the concrete

EPD:

Concrete admixtures – Plasticisers and Superplasticisers
EPD-EFC-20210198-IBG1-EN

Dosage:

0.5 - 2.0 wt.% of the binding agent content
The quantity to use depends on the required effect, cement grade and type of concrete.
Please call us for technical advice.

Prior to use, a suitability test according to EN 206-1 or any applicable standards or norms relevant in your country is required.

Processing:

Is added together with the aggregates or, if the aggregates are highly absorbent, to the finished concrete mix.

In the case of very dry or highly absorbent aggregates, the addition is made with the mixing water.

Specifications:

Appearance: liquid
Colour: yellowish
Density: 1.06 ± 0.02 g/ml

Storage:

Under normal storage conditions (closed container, 20 °C) minimum shelf-life 12 months
Protect from frost, direct sunlight and contamination.

Packaging:

Containers 1000 kg, Barrels 200 kg, Canisters 20 kg
Other delivery quantities on request

Safety Rules:

See EC safety data sheet.

The product should only be used with suitable protective gloves (EN 374) and safety goggles (EN 166).

When used, ensure good ventilation (5 to 15 air exchange per hour).

Assistance:

Please contact our Technical Application Centre.

Industrial use:

Recommended frequency and duration of use:

480 minutes/day

200 days/year

Environmental Exposure:

Do not allow undiluted product or large quantities of it to reach ground water, water bodies or the sewage system.