

REBAment WR (BV) NEXT

Concrete plasticizer according to EN 934-2:T2

Industrial use

Product No.: 230028000

Product Information:

Sustainability Assessment:

Reducing the water-cement ratio and increasing the durability of the concrete

EPD:

Concrete admixtures – Plasticisers and Superplasticisers

EPD-EFC-20210198-IBG1-EN

Properties:

- good water retention value
- plasticizing
- easier workability of the concrete and more readiness to compact

Application:

concrete products

Efficiently lowering the clinker factor makes it possible to reduce CO₂ emissions.

A reduction in the clinker factor in cement from 0.73 to 0.5 means a reduction of > 200 kg/CO₂ per tonne of cement (calculation basis = approx. 750 kg to 800 kg CO₂ per tonne of clinker).

The life cycle assessment data and the other contents of the sample EPD can be used to assess the sustainability of buildings in which the product has been installed.

Is added together with the aggregates or, if the aggregates are highly absorbent, to the finished concrete mix.

In the case of very dry or highly absorbent aggregates, the addition is made with the mixing water.

At low temperatures, natural processes can lead to cloudiness. As a rule, however, the cloudiness disappears with gentle heating and stirring without any loss of quality.

Dosage:

0.2 - 0.5 wt.% of the binding agent content

The quantity to use depends on the required effect, cement grade and type of concrete.

Please call us for technical advice.

Prior to use, a suitability test according to EN 206-1 or any applicable standards or norms relevant in your country is required.

Specifications:

Appearance: liquid
Colour: whitish
Density: 1.00 ± 0.02 g/ml

Storage:

Under normal storage conditions (closed container, 20 °C) minimum shelf-life 12 months

Protect from frost, direct sunlight and contamination.

Stir before use. Close well after use.

Packaging:

Containers 1000 kg, Drums 200 kg, Canisters 20 kg

Other delivery quantities on request

Safety Rules:

See EC safety data sheet.

The product should only be used with suitable protective gloves (EN 374) and safety goggles (EN 166).

When used, ensure good ventilation (5 to 15 air exchange per hour).

Assistance:

Please contact our Technical Application Centre.

Industrial use:

Recommended frequency and duration of use:

480 minutes/day

200 days/year

Environmental Exposure:

Do not allow undiluted product or large quantities of it to reach ground water, water bodies or the sewage system.